



## 3/4mm solid polycarbonate

3/4mm solid polycarbonate sheet has UV protection on both sides, offering excellent light diffusion with transparency. It has excellent impact resistance and fire performance, ease of installation and is an excellent candidate for a wide variety of interior and exterior applications.



**Solid polycarbonate can also be used as COVID protection screens.**

### Chemical resistance

3/4mm solid polycarbonate has sufficient resistance to most chemical substances encountered in normal exterior use. In applications where the product will come into contact with aggressive chemicals, specific (application related) testing of the material is always advised. It is essential to check the compatibility before use.

### Fire performance

3/4mm solid polycarbonate is Class 1Y fire rated and has passed the BS 475 Pt7 test.

### Regulatory information

This product is not considered dangerous under EC Directives 67/548/EEC, as amended. This MSDS has been prepared in accordance with EU Directive 91/155/EEC, as amended by 93/112 EC.

### Maintenance and care

3/4mm solid polycarbonate should be treated with care.

1. Use generous amounts of lukewarm water to rinse sheet and soften dried dirt.
2. Make up a solution of lukewarm water and ordinary household cleaner or a mild soap, and use this to wash sheet; a sponge or soft cloth should be used to gently remove dirt and grime.
3. Rinse with clean lukewarm water and repeat washing if necessary.
4. After final rinse, dry off with a soft cloth.



3/4mm solid polycarbonate sheets are particularly vulnerable to scratching.

- Do not scrub with brushes, abrasive materials or sharp instruments as these will mark the surface.
- Never use solvents, alkaline cleaners, thinner or abrasive cleaners.
- Never steam clean. Use low pressure if pressure washing.
- Never use acetone, petrol, benzene or solvents containing Butyl Cellosolve or Isopropanol.
- Incorrect cleaning which in any way damages the sheet will automatically render all warranties void.

Property	Test Method	Unit	Value
<b>Physical</b>			
Specific Gravity	ISO 1183	g/cm3	1.20
Water Absorption, 23°C, 24 hours	ISO 62	%	0.10
Equilibrium	ISO 62	%	0.35
<b>Mechanical</b>			
Tensile Stress, yield	ISO 527	N/mm2	60
Tensile Modulus	ISO 527	N/mm2	2350
Tensile Strain, yield	ISO 527	%	6
Tensile Strain, break	ISO 527	%	120
Flexural Stress, yield	ISO 178	MPa	90
Flexural Modulus	ISO 178	MPa	2300
<b>Impact</b>			
Izod Impact, notched 20°C	ISO 180/1A	kJ/m2	65
-40°C		J	>37
<b>Thermal</b>			
Vicat Softening Temperature, rate B/120	ISO 306	°C	148
Ball Pressure Test 75°C-125°C	IEC 335-1	-	Passes
Mould Shrinkage	ASTM D1955	%	0.6-0.8
Thermal Expansion	DIN 53752	1/ °C	7.10-5